

Rust Inhibited

A lithium soap thickened, light viscosity synthetic hydrocarbon grease intended for electrical switch contacts. Enhanced temperature stability for light mechanical applications.

Ford: WSD-M1C234-A2

Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-54 to 125	
Thickener		Lithium Soap	
Base Oil	Type	Polyalphaolefin	
	Kinematic Viscosity	40°C	33 cSt
		100°C	6 cSt
	Viscosity Index		141
	Flash Point	°C	250
	Pour Point	°C	-65
Typical Properties of the Grease		Typical Value	Test Method
Color, Appearance		Light Tan, Smooth	
Penetration (1/10 mm)	Worked	60X	273
	Unworked		266
	NLGI Grade		2
Density		25°C	0.83 g/cm ³
Oil Separation	24 hour(s)	100°C	2.9
Evaporation	24 hour(s)	100°C	0.07 %

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1506)