

## Copper Deactivator, UV Tracer

A silica thickened, medium viscosity, synthetic hydrocarbon grease for lubrication and protection of electrical contacts. Benefits include good water resistance.

Ford: WSB-M1C239-A, GM: 9986087, DaimlerChrysler: MS-9469

Lubricant Properties		Typical Value	Test Method
<b>Recommended Service Range (°C)</b>		-40 to 135	
<b>Thickener</b>		Silica	
<b>Base Oil</b>	Type	Polyalphaolefin	
	Kinematic Viscosity	100°C	39.4 cSt
		40°C	400 cSt
		-30°C	213788.5 cSt
	Viscosity Index		147.5
	Flash Point	°C	321
	Pour Point	°C	-36
Typical Properties of the Grease		Typical Value	Test Method
<b>Color, Appearance</b>		Water White, Smooth	
<b>Penetration (1/10 mm)</b>	Unworked		266
	Worked	60X	286
		10K	303
		100K	311
	NLGI Grade		2
<b>Density</b>		25°C	0.88
<b>Oil Separation</b>	24 hour(s)	100°C	1.5 %
<b>Evaporation</b>	24 hour(s)	100°C	0.3

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1504)