

A medium viscosity, completely fluorinated oil possessing very wide temperature capability, excellent oxidation resistance, excellent plastic and elastomer compatibility and resistance to aggressive chemicals.

NSF H-1 Registered #142528

Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-65 to 250	
Color, Appearance		Clear	
Base Oil	Type	Perfluoropolyether	
	Kinematic Viscosity	40°C 100°C	150 cSt 45 cSt
	Viscosity Index	340	ASTM D-2270
	Flash Point	°C	None, non-flammable ASTM D-92
	Pour Point	°C	-65 ASTM D-97
Evaporation	24 hour(s)	150°C	0.01 % NYE CTM
		200°C	0.1 % NYE CTM
Density	25°C	1.88 g/cm ³	ASTM D-1480

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1509)