

AS1805 (1088R)

1 Part Neutral cure high temperature thixotropic adhesive sealant

Introduction

AS1805 is a non-corrosive, 1-part, room temperature vulcanising (RTV) silicone rubber. It is one of a new family of products called acetone cure sealants that are solvent free. It exhibits excellent primerless adhesion to many substrates. The product is cured rapidly in contact with atmospheric moisture to a tough rubber. AS1805 does not corrode copper or its alloys and exhibits excellent primerless adhesion when fully cured.

Key Features

- Very good temperature resistance to 300°C
- Excellent adhesion to many substrates
- Fast skinning
- Solvent free

How to use

AS1805 is ready for use. If supplied in cartridges it can be applied using either manual or pneumatic dispensers. It can also be applied from bulk containers using conventional drum dispensing equipment.

Application and Cure

All surfaces to which AS1805 is to be applied should be clean, dry and free from grease, dirt, and loose material. Priming of surfaces is not normally required. If AS1805 is being employed as an adhesive, it should be applied to one clean surface and the other clean surface brought into contact with it within 15 to 20 seconds. The recommended thickness of the sealant joint is 1 to 2mm for optimum bond strength. Joints should be left undisturbed for at least 24 hours, but preferably longer to effect sufficient depth of cure. Full cure requires 7 days.

Health and Safety – Material Safety Data Sheets available on request.

Packages - 310 ml cartridges. Arrangements can be made to supply in bulk containers

Storage and Shelf Life – Expected to be 12 months in cartridges and 9 months in bulk, unopened containers.

Property

Uncured Product

Colour:	Red
Appearance:	Thixotropic Paste
Tack Free Time:	4 minutes *
3mm Cure Through:	8 hours *
Extrusion Rate:	180g / minute
* measured at 23+/-2°C and 65% relative humidity.	

Cured Elastomer

(after 7 days cure at 23+/-2°C and 65% relative humidity)

Tensile Strength:	BS903 Part A2	1.7 MPa
Elongation at Break:	BS903 Part A2	270 %
Hardness:	ASTM D 2240-05	50° Shore A
Specific Gravity:	BS 903 Part A1	1.10
Linear Shrinkage:		0.5 %
Thermal Conductivity:		0.20 W/mK
Coefficient of Thermal Expansion:		
Volumetric		884 ppm / °C
Linear		295 ppm / °C
Min. Service Temperature:		-50 °C
Max. Service Temperature:	AFS 1540B	300 °C

Electrical Properties

Volume Resistivity:	ASTM D-257	3.5x10 ¹⁵ Ω.cm
Dielectric Strength:	ASTM D-149	21 kV/mm
Dielectric Constant at 1MHz:	ASTM D-150	3.05
Dissipation Factor at 1MHz:	ASTM D-150	1.2x10 ⁻³

Adhesion Testing

Overlap Shear Strength:	ASTM D 1002	kg/cm ²
Copper		2.80
Aluminium		3.74
Stainless Steel 304		3.12
Polycarbonate		

Customers are advised to carry out their own tests on clean, degreased substrates to ensure satisfactory adhesion is achieved.

Stress cracking can appear on some grades of polycarbonate. Customers are advised to carry out initial testing to ensure product compatibility.

All values are typical and should not be accepted as a specification.

Revision Date: 01/0302016

The information and recommendations in this publication are to the best of our knowledge reliable. However nothing herein is to be construed as a warranty or representation. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.